



### Bitumen grade 60/70

Name	Specification	Test Method
Specific Gravity @ 25/25 C	1.01-1.06	D-70
Penetration @25C	60/70	D-5
Softening Point C	49/56	D-36
Ductility @25 C	100 MIN	D-113
Loss On Heating (WT)%	0.2 MAX	D-6
Drop In Penetration After Heating %	20 MAX	D-6 & D-5
Flash Point C	250MIN	D-92
Solubility In CS2 (WT)%	99.5 MIN	D-4
Spot Test	NEGATIVE	*A.A.S.H.O.T.102