

Oxidized Bitumen 115/15

| Name | Specification | Test Method |
|-------------------------------|---------------|-------------|
| Specific Gravity @ 25/25 C | 1.05 Approx | D-70 |
| Penetration @25C | 10/20 | D-5 |
| Softening Point C | 110/120 | D-36 |
| Ductility @25 C | 1.5 MIN | D-113 |
| Loss On Heating (WT)% | 0.2 MAX | D-6 |
| Flash Point C | 260 MIN | D-92 |
| Solubility In CS2 (WT)% | 99 MIN | D-4 |

