

Oxidized Bitumen 115/15

Name	Specification	Test Method
Specific Gravity @ 25/25 C	1.05 Approx	D-70
Penetration @25C	10/20	D-5
Softening Point C	110/120	D-36
Ductility @25 C	1.5 MIN	D-113
Loss On Heating (WT)%	0.2 MAX	D-6
Flash Point C	260 MIN	D-92
Solubility In CS2 (WT)%	99 MIN	D-4

